






GENERAL STREET CONSTRUCTION NOTES:

1. PAVEMENT EDGES SHALL BE SLIGHTLY ROUNDED TO APPROXIMATELY 1/4".
2. ASPHALTIC CONCRETE JOINING P.C.C.P. OR ASPHALTIC CONCRETE SHOULDER: THE ASPHALT JOINT SHALL BE SAW CUT AND CONSTRUCTED IN ACCORDANCE WITH SECTION I-1, DRAWING RW3.
3. FOR SECTIONS C-C, E-E, F-F, G-G, H-H, I-I, J-J, AND K-K SEE DRAWING RW3.
4. ALL JOINTS ARE TO BE USED WHERE SHOWN ON THIS SHEET OR AS SHOWN ELSEWHERE IN THE PLANS OR AS OTHERWISE DIRECTED BY THE ENGINEER.
5. ON TYPE EJ JOINTS, SPOT WELD ALTERNATE ENDS OF DOWEL BARS TO DOWEL BASKETS AND PLACE EXPANSION TUBES ON FREE ENDS OF DOWEL BARS, (SECTION A-A).
6. TYPE EJ JOINTS SHALL BE SEALED WITH PREFORMED ELASTOMERIC COMPRESSION JOINT SEALS CONFORMING TO SUBSECTION 1005.03 OF DOTD LOUISIANA STANDARD SPECIFICATIONS FOR ROADS AND BRIDGES, LATEST EDITION. THE SEALS SHALL HAVE A NOMINAL WIDTH OF 1-1/4" BEFORE COMPRESSION. JOINTS SHALL BE CLEANED PRIOR TO SEALING.
7. FOR DESIGN SPEEDS OF 45 MPH OR GREATER:
 - A. TYPE LJ JOINTS SHALL BE SAW CUT AND CONSTRUCTED AS IN DETAIL "F" DRAWING RW3. THE JOINT SHALL BE SAW CUT AND CLEANED PRIOR TO SEALING WITH A JOINT SEALANT CONFORMING TO SUBSECTION 1005.02(b) OR (c) OF THE AFOREMENTIONED DOTD SPECIFICATIONS.
 - B. TYPE TCJ OR CJ SHALL BE SAW CUT AS SHOWN IN DETAIL "C" OR "D" DRAWING RW3 AND TO THE DEPTH SHOWN IN TABLE 1. THE JOINT SHALL BE SAND BLASTED AND CLEANED IMMEDIATELY PRIOR TO SEALING. THE INITIAL CUT SHALL BE MADE WITH 1/8" MINIMUM BLADE. THE SEALANT SHALL BE A PREFORMED ELASTOMERIC SEAL IN ACCORDANCE WITH SUBSECTION 1005.03 OR A SILICONE SEALANT IN ACCORDANCE WITH SUBSECTION 1005.02(c) OF THE AFOREMENTIONED DOTD SPECIFICATIONS.
8. FOR DESIGN SPEEDS OF LESS THAN 45 MPH:
 - A. TYPE LJ JOINTS SHALL BE SAW CUT AS DESCRIBED IN 7(A).
 - B. TYPE TCJ OR CJ SHALL BE CONSTRUCTED AS FOLLOWS:
 - (1) CONSTRUCTED AS DESCRIBED IN 7(B).
 - (2) WITH A REMOVABLE FORMING DEVICE AS SHOWN IN DETAILS "A" AND "B" DRAWING RW3. THE JOINT SHALL BE SAND BLASTED AND CLEANED IMMEDIATELY PRIOR TO SEALING AND MAY REQUIRE SAWING TO ACHIEVE PROPER RESERVOIR DIMENSIONS.
 - (3) WITH A COMBINATION JOINT FORMER/SEALER AS SHOWN IN DETAIL "F" DRAWING RW3. THE SEALER SHALL CONFORM TO SUBSECTION 1005.04 AND BE INSTALLED IN ACCORDANCE WITH SUBSECTION 601.09(c)(3) OF THE AFOREMENTIONED DOTD SPECIFICATIONS AND NO ADDITIONAL SEALANT IS REQUIRED.
9. EXCEPT AS NOTED BELOW, DOWEL BARS & TIE BARS SHALL BE HELD IN PLACE BY SUPPORTS SIMILAR TO THE ONES SHOWN, OR APPROVED EQUALS. APPROVED MECHANICAL PLACEMENT OF DOWEL BARS AND TIE BARS WILL BE ALLOWED WITH ALL PAVING METHODS. WHEN DOWEL BAR BASKETS ARE USED, APPROXIMATELY THE CENTER 7" OF SPACER WIRES, THAT SPANS ACROSS THE JOINT, SHALL BE CLIPPED AND REMOVED AFTER STAKING BASKETS IN PLACE.
10. INSTALL GEOTEXTILE FABRIC UNDER ALL TCJ, CJ, AND EJ JOINTS WHEN CONCRETE PAVEMENT IS PLACED ON UNSTABILIZED OR UNTREATED BASE COURSES OR SUBBASES. WHEN DOWEL BARS ARE MECHANICALLY IMPLANTED, THE GEOTEXTILE FABRIC SHALL BE ANCHORED TO THE BASE COURSE WITH PINS.
11. WHEN CONSTRUCTING CONCRETE CURB AND GUTTER ADJACENT TO NEW P.C.C. PAVEMENT, USE TYPE LCJ JOINT. WHEN ADJACENT TO EXISTING P.C.C. PAVEMENT, USE TYPE LBJ JOINT. THE FIRST LOAD TRANSFER DEVICE SHALL BE INSTALLED 18" FROM THE PAVEMENT EDGE.
12. TRANSVERSE EXPANSION JOINTS SHALL NOT BE USED FOR CONSTRUCTION JOINTS.
13. CONCRETE SHOULDERS:
 - A. CONSTRUCT TCJ JOINTS IN ACCORDANCE WITH SECTION B-B.
 - B. CONSTRUCT LCJ JOINTS IN ACCORDANCE WITH TYPE LCJ DETAIL ON THIS SHEET AND LJ JOINTS IN ACCORDANCE WITH SECTION D-D.
 - C. USE THE MAXIMUM SHOULDER THICKNESS WHEN DETERMINING DOWEL BAR AND TIE BAR SIZES IN TABLE 1.
 - D. WHEN SKEWED JOINTS ARE USED ON MAINLINE PAVING THE SHOULDER TCJ JOINTS MAY BE SKEWED OR CONSTRUCTED AT 90°.
 - E. SHOULDER JOINTS AND JOINT MATERIALS WILL MATCH THE MAINLINE.
 - F. HEIGHT OF DOWEL BASKETS WILL BE BASED ON THE SHOULDER THICKNESS. ALSO VARYING HEIGHT DOWEL BASKETS WILL BE ALLOWED.
14. TIE BARS SHALL NOT BE PLACED WITHIN 18" OF CONTRACTION OR EXPANSION JOINTS.
15. FOR REINFORCED STEEL, SEE DOTD SPECIFICATIONS SECTION 1009.

TABLE 1
(ALL DIMENSIONS IN INCHES)

PAVEMENT THICKNESS T	SMOOTH DOWEL BARS			DEF. TIE BARS			MINIMUM DEPTH OF JOINT		KEYWAY	
	SIZE	LENGTH	SPACING	SIZE	LENGTH	SPACING	TCJ & CJ ±1/4"	LJ ±1/4"	A ±1/4"	B ±1/4"
7 OR LESS	1	18	12	1/2	24	24	2-1/2	2-1/2	ALLOW 7"	
8	1-1/4	18	12	1/2	24	24	3	3	2-1/2	1-1/4
9	1-1/4	18	12	1/2	24	24	3	3-1/2	2-1/2	1-1/4
10	1-1/2	18	12	1/2	24	24	3-1/2	4	2-1/2	1-1/4
11	1-1/2	18	12	5/8	30	24	3-1/2	4	2-1/2	1-1/4
12	1-1/2	18	12	5/8	30	24	4	4-1/2	3	1-1/2
13	1-1/2	18	12	5/8	30	24	4	4-1/2	3	1-1/2
14	1-1/2	18	12	5/8	30	24	4-1/2	5	3	1-1/2

⊗ FOR CONC. SHOULDERS, "T" IS THE THICKNESS AT PAVEMENT EDGE.



 CITY OF NEW ORLEANS DEPARTMENT OF PUBLIC WORKS ENGINEERING DIVISION	TYPICAL ROADWAY SECTIONS FOR STREET CONSTRUCTION		DRAWING No. RW2
	THE SELECTION AND USE OF THESE DETAILS, WHILE DESIGNED IN ACCORDANCE WITH GENERALLY ACCEPTED ENGINEERING PRINCIPLES AND PRACTICES, IS THE SOLE RESPONSIBILITY OF THE USER AND SHOULD NOT BE USED WITHOUT CONSULTING A LOUISIANA REGISTERED PROFESSIONAL ENGINEER.	DRAWN BY: N. SCHNEIDER DATE: 2/5/2015	